



RAVENOL BIO-Hydraulikoel HEES 68



ART.-NR. 1321106

| 1321106-208

SPECIFICATIONS REXROTH BOSCH GROUP: RE / RD 90221-01/02.10, SP TECHNICAL RESEARCH INSTITUTE, SWEDEN (SWEDISH STANDARD 15 54 34), FULFILS THE REQUIREMENTS OF "BLAUEN ENGEL" (ENVIRONMENTAL FRIENDLY)

FABRICATION BIODEGRADABLE

RECOMMENDATIONS VDMA 24568/ ISO 15380

Hydraulicfluid based on easily biogedradable ester.

RAVENOL BIO-Hydraulikoel HEES 68 is based on synthetic, easily biodegradable ester and a powerful, environmentally friendly combination of additives which gives the product excellent properties regarding oxidation stability, corrosion, low temperatures as well as EP behaviour. Compared with products of vegetable triglyceride base, **RAVENOL BIO-Hydraulikoel HEES 68** has much better high temperature oxidation stability.

Application Notes

RAVENOL BIO-Hydraulikoel HEES 68 is used wherever there is the danger of hydraulic fluid leaking into the ground or waste water. This includes all equipment operating in or near areas of water purification or water protection or near surface water, such as e.g. sewage treatment plants, dredging ships and floating dredges, lock hydraulics and river weirs, pipe and tunnel diving machines, - hydraulic aggregates in forests and on plains, earth moving machines in water collecting areas, forestry machines.

Characteristics

RAVENOL BIO-Hydraulikoel HEES 68 offers:

- Meets the requirements of the Federal Ministry for consumer protection, alimentation and agriculture regarding good biodegradability and technical specifications.
- On account of the used raw materials, **RAVENOL BIO-Hydraulikoel HEES 68** is classified as water polluting class NWG (not water-polluting) – German classification.

Property	Unit	Data	Audit
Density at 20°C	kg/m ³	920	EN ISO 12185
Colour		gelbbraun	visual
Viscosity at 100°C	mm ² /s	12,7	DIN 51 562
Viscosity at 40°C	mm ² /s	68,0	DIN 51 562
Viscosity index VI		190	ISO 2909



Property	Unit	Data	Audit
Pourpoint	°C	-39	DIN ISO 3016
Flash point (COC)	°C	312	DIN ISO 2592
Corrosive Action		1A	DIN EN ISO 2160
Foaming behavior SEQ I	ml	10/0	ISO 6247
Foaming Behavior SEQ II	ml	5/0	ISO 6247
Foaming behavior SEQ III	ml	5/0	ISO 6247
Air release property at 50°C max.	min.	2	ISO 9120
Part of renewable raw materials	%	85	ASTM D6866

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 20. November 2019