



RAVENOL Kompressorenoel VDL 32



ART.-NR. 1330097

20 L | 1330097-020

SPECIFICATIONS ISO/DP 6521 (DAA, DAB, DAH, DAG) | DIN 51 506 VDL-ÖLE

FABRICATION MINERAL

RECOMMENDATIONS DIE ANFORDERUNGEN FÜR VBL- UND VCL-ÖLE WERDEN BEI WEITEM ÜBERTROFFEN. | ATLAS COPCO | ALUP | COMPAIR | FIAC | FINI | KAESER

RAVENOL Kompressorenoel VDL 32 meets the high requirements of DIN 51 506. Specially designed with high quality, age-resistant base oils.

RAVENOL Kompressorenoel VDL 32 has a good adhesion, is water repellent and wear reducing. As many compressors operate at high temperatures, the oil should have good aging resistance at very low residue formation.

RAVENOL Kompressorenoel VDL 32 provides a secure lubrication not only in the upper temperature range, also in the cold state of the compressor to achieve a reduction of wear. By selected and coordinated additive composition the tendency to coking and the formation of flammable residues is minimized.

Application Notes

RAVENOL Kompressorenoel VDL 32 can be used in stationary and mobile compressors with discharge temperatures up to 220°C.

RAVENOL Kompressorenoel VDL 32 can also be used for lubrication of engines and diesel engines where the manufacturer does not stipulate any HD motor oil.

Characteristics

RAVENOL Kompressorenoel VDL 32 offers:

- Excellent aging resistance
- Reliable wear protection
- Excellent viscosity-temperature behavior
- Very good cold starting properties
- Low coking tendency
- Neutral towards sealing materials.

Property	Unit	Data	Audit
Density at 20°C	kg/m ³	854,0	EN ISO 12185
Colour		gelb	visual



Property	Unit	Data	Audit
kinematic viscosity at 100°C	mm ² /s	5,4	DIN 51562-1
Base oils viscosity at 40°C	mm ² /s	29,3	DIN 51562-1
Viscosity index VI		122	DIN ISO 2909
Pourpoint	°C	-27	DIN ISO 3016
Flash point	°C	222	DIN ISO 2592

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 24. January 2020