



RAVENOL Super EP-Langzeitfett



ART.-NR. 1340104

1 kg | 1340104-001
5 kg | 1340104-005
10 kg | 1340104-010
15 kg | 1340104-015
25 kg | 1340104-025
100 g | 1340104-100
180 kg | 1340104-180
200 g | 1340104-200
400 g | 1340104-400

SPECIFICATIONS DIN 51 502: KP2K-30 | ISO 6743 PART 9: ISO-L-XCCFB2
APPROVALS LOVAT LOV-204

RAVENOL Super EP-Langzeitfett is a high quality grease with heavy-metal-free EP additives. This generation of additive packages ensures a long life of the parts to be lubricated and reduces maintenance costs.

RAVENOL Super EP-Langzeitfett is due to its smooth structure is easily conveyed.

RAVENOL Super EP-Langzeitfett is based on high-quality base oil by using lithium soaps (Li-12-hydroxy stearate) as thickener. Due to this they avail of an outstanding work resistance. Furthermore, **RAVENOL Super EP-Langzeitfett** contain additives to improve the rust and corrosion-preventing behaviour.

Application Notes

RAVENOL Super EP-Langzeitfett is used for the lubrication of heavily loaded plain and rolling bearings under the influence of moisture, vibration and shock loads. The standard applies to the lubrication of chassis, wheel bearings and universal joints in the automotive sector as well as machinery and general industry, construction industry, agriculture.

Characteristics

RAVENOL Super EP-Langzeitfett offers:

- Universal application, multi-purpose mixed pattern for machinery
- Excellent impact and wear-EP
- Very good oxidation and corrosion protection even in the presence of moisture
- Very good mechanical stability
- Excellent water resistance
- Long service life and thus extended lubrication intervals possible
- Very good resistance to aging
- Good pumpability, even at low temperatures



Property	Unit	Data	Audit
Colour		braun	visual
Thickener		Lithium-Komplexseifen	-
NLGI-Class		2	DIN 51 818
DIN-Product-Classification		KP2K-30	DIN 51 502
ISO-Product-Classification		ISO-L-XCCFB2	ISO 6743 P.9
Working Temperature	°C	-30 / +120	DIN 51 825
Short Term up to	°C	130	-
Worked Penetration 60 strokes	mm/10 bei 25°C	265-295	ISO 2137
Corrosion (SKF Emscor dist. Water)	Corr. Degree	1	DIN 51 802
Dropping Point	°C	>180	DIN ISO 2176
Copper Corrosion (24h/120°C)		1	DIN 51 811
Water Resistance (3h/90°C)	°C	1-90	DIN 51 807 T.1
VKA Pressure Carrying Capacity	N	2400 - 2600	DIN 51 350 T.4
Kinematic Viscosity (Base Oil)	mm ² /s bei 40°C	130	DIN 51562-1

All information correspond to the best of our knowledge to the actual situation of the cognitions and our development. Subject to alterations. All references made to DIN-norms are only for the description of the goods. There is no guarantee. In case there will be any problems please contact the technical service.

Release: : 12. January 2015